



Certificate no.:

Revision No:

# TYPE APPROVAL CERTIFICATE

---

---



Job ID:  
 Certificate no.:  
 Revision No:

Woven Rovings: , , , , and .

Legends:  
 E: E-Glass  
 WR: Woven Roving  
 270, 360, 500, 580, 800: Weight per unit area, g/m<sup>2</sup>

The following indicative properties have been verified by Type Testing of laminates:

Tensile Strength – warp	ISO 527-1,4	409.04	425.57	457.28	mean	MPa
Tensile Modulus – warp	ISO 527-1,4	24.04	25.28	22.80	mean	GPa
Tensile Strength – weft	ISO 527-1,4	395.67	350.77	440.20	mean	MPa
Tensile Modulus – weft	ISO 527-1,4	23.70	23.65	24.17	mean	GPa
Fibre content by weight	ISO 1172	61.13 (0) 61.89 (90)	61.16 (0) 61.22 (90)	61.65 (0) 61.32 (90)	mean	%
Resin	TM-107					
Curing Procedure used for Type Testing	24 hrs at room temperature, 4 hrs at 80°C					

Tensile Strength – warp	ISO 527-1,4	459.29	511.93	440.15	mean	MPa
Tensile Modulus – warp	ISO 527-1,4	24.77	26.62	23.53	mean	GPa
Tensile Strength – weft	ISO 527-1,4	400.52	388.37	364.75	mean	MPa
Tensile Modulus – weft	ISO 527-1,4	23.00	24.25	19.47 <sup>1)</sup>	mean	GPa
Fibre content by weight	ISO 1172	61.64 (0) 61.19 (90)	64.76 (0) 64.51 (90)	62.61 (0) 62.36 (90)	mean	%
Resin	TM-107					
Curing Procedure used for Type Testing	24 hrs at room temperature, 4 hrs at 80°C					

(0): fibre content for warp laminates  
 (90): fibre content for weft laminates

<sup>1)</sup> Value is below stated acceptance criteria of CP-0467, Table 3.

Legends:  
 mean = Mean of Type Test results

The product complies with the applicable requirements of DNV and is compatible to the laminating resin.

Any significant changes in design and / or quality of the material will render the approval invalid.

1. Assessment Report from DNV Shanghai of 2024-10-29.
2. ISO 9001 Certificate, DEKRA Registration No. 20319142/1-1.
3. Jushi Group Co., Ltd. Testing Center, Report Nos. BG241011107 Rev.A (EWR270), BG241011108 Rev.A (EWR360), BG241011109 Rev.A (EWR500), BG241011110 Rev.A (EWR580), BG241011111 Rev.A (EWR600), BG241011112 Rev.A (EWR800) of 2024-10-11.
4. Assessment Report from DNV GL Shanghai of 2019-05-10.
5. Testing Center, Jushi Group Co., Ltd. Report Nos. BG190325101 (EWR270), BG190325102 (EWR360), BG190325103 (EWR500), BG190325104 (EWR580), BG190325105 (EWR600), BG190325106 (EWR800) of 2019-03-25.
6. ISO 9001 Audit Report (DEKRA).
7. Application for Type Approval of 2019-03-25.
8. Email from DNV GL Shanghai of 2015-05-05, including Assessment Report of 2015-05-05 and Application Letter from Jushi of 2015-01-29.



Job ID:  
Certificate no.:  
Revision No:

9. Email from DNV Shanghai of 2011-05-09, including Survey Report of 2011-05-09, Declaration of Conformity from Jushi of 2011-04-08, Application Letter from Jushi of 2011-04-08 and DNV Approval Documents 2011 issued by Jushi, Test Report Nos. BG110402004 and BG110402005 of 2011-04-02.

Type Testing carried out in accordance with .

Product shall be marked with *manufacturer's name*: and *type designation*.

The marking is to be carried out in such a way that it is visible, legible and indelible. The marking of product is to enable traceability to the DNV Type Approval Certificate.

The scope of the Periodical Assessment is to verify that the conditions stipulated for the Type Approval is complied with and that no alterations are made to the product design or choice of materials.

Periodical assessments (for Certificate Retention / Certificate Renewal) shall be performed according to DNV-CP-0338.

This certificate is only valid if required Periodical assessments are carried out with satisfactory results. To check the validity of this certificate, please look it up in <https://approvalfinder.dnv.com>

END OF CERTIFICATE